

AD-A097 232

AKRON UNIV OH INST OF POLYMER SCIENCE
THRESHOLD TEAR STRENGTH OF SOME MOLECULAR NETWORKS.(U)
APR 81 A N GENT, R H TOBIAS N00014

F/6 11/9


N00014-76-C-0408

NL

UNCLASSIFIED TR-12

$$\frac{1}{\Delta t} \left(\frac{1}{\Delta t} \right)$$

END
DATE
FILMED
5-81
DTIC



MICROCOPY RESOLUTION TEST CHART
 NATIONAL BUREAU OF STANDARDS-1963-A

LEVEL II

12

13 S

OFFICE OF NAVAL RESEARCH

Contract ¹⁵ N00014-76-C-0408

Project NR 092-555

⁹ Technical Report No. ¹⁴ TR-12

⁶ THRESHOLD TEAR STRENGTH OF SOME MOLECULAR NETWORKS.

by

¹⁰ A. N. Gent ~~and~~ R. H. Tobias
Institute of Polymer Science
The University of Akron
Akron, Ohio 44325

¹¹ 3 Apr 1981

¹² 122

DTIC
ELECTE
S APR 02 1981 D
F

Reproduction in whole or in part is permitted
for any purpose of the United States Government

Approved for Public Release; Distribution Unlimited

DTIC FILE COPY

401069

Q1 4

2 147

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER Technical Report 12	2. GOVT ACCESSION NO. AD-A097	3. RECIPIENT'S CATALOG NUMBER 232
4. TITLE (and Subtitle) Threshold Tear Strength of Some Molecular Networks		5. TYPE OF REPORT & PERIOD COVERED Technical Report
		6. PERFORMING ORG. REPORT NUMBER N00014-76-C-0408
7. AUTHOR(s) A. N. Gent and R. H. Tobias		8. CONTRACT OR GRANT NUMBER(s) NR 092-555
9. PERFORMING ORGANIZATION NAME AND ADDRESS Institute of Polymer Science The University of Akron Akron, Ohio 44325		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS
11. CONTROLLING OFFICE NAME AND ADDRESS Office of Naval Research Power Program Arlington, Virginia 22217		12. REPORT DATE April 3, 1981
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		13. NUMBER OF PAGES 13
		15. SECURITY CLASS. (of this report) Unclassified
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report) Approved for public release; distribution unlimited		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES Submitted for publication in: ACS Polymer Preprints		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Crosslinking, Endlinking, Elastomers, Fracture, Polydimethylsiloxane, Tear Energy, Strength		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) The tear strength of polydimethylsiloxane (PDMS) networks was found to be only about one-third as large as that of polybutadiene (PB) or polyisoprene (PI) networks of similar M_c when the tear strength was measured under threshold conditions, i.e., at high temperatures, low rates of tearing, and with swollen samples. This striking difference in strength is attributed to the smaller length and extensibility of PDMS molecules in comparison with PB or PI molecules of the same molecular weight. Networks formed by trifunctional or tetrafunctional endlinking reactions with difunctional PDMS polymers were found to be		

DD FORM 1473
1 JAN 73

EDITION OF 1 NOV 65 IS OBSOLETE
S/N 0102-LF-014-6601

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

only slightly stronger under threshold conditions, by up to 30 per cent, than PDMS networks formed by random crosslinking to the same M_c . Endlinked PB networks were found to have substantially the same threshold strength as randomly-linked PB networks of the same M_c . Thus, the threshold tear strength does not appear to depend strongly upon the uniformity of network strand lengths.

THRESHOLD TEAR STRENGTH OF SOME MOLECULAR NETWORKS

by

A. N. Gent and R. H. Tobias

Introduction

When dissipative processes are minimized, the tear strength of elastomeric materials is found to reach a lower limit, termed here the threshold strength (1,2). Experimentally, the threshold strength is reached at high temperatures, at low rates of tearing and when the material is highly swollen with a low-viscosity liquid. Its magnitude has been predicted theoretically from the length of the molecular strands comprising the network and the dissociation energy of the chemical bonds comprising the strand (3). Expressed as the energy T_0 required to tear through a unit area of the material, the theoretical result takes the form

$$T_0 = KM_C^{1/2} \quad (1)$$

where M_C is the mean molecular weight of the network strands and K is a constant involving the mass, length and effective flexibility of a monomeric unit, the density of the polymer and the dissociation energy of the relevant bonds. For C-C molecular strands K is predicted to be about $0.3 \text{ J/m}^2/(\text{molecular weight unit})^{1/2}$. Experimental values of T_0 for randomly-crosslinked networks of polybutadiene were found to be consistent with equation 1, when K was given a somewhat higher value, about $1.0 \text{ J/m}^2/(\text{molecular weight unit})^{1/2}$. Thus, apart

tion For

GRA&I

TAB

enced

fiction

dy

Distribution/

Availability Codes

Avail and/or

Special

Dist

A

(2)

from this numerical discrepancy, the threshold strength of polybutadiene networks is reasonably well accounted for. We now address two further aspects of threshold strength. Does the tear strength of other elastomers, of different chemical type, conform to equation 1? And are randomly-crosslinked materials weaker than more regular networks, prepared, for example, by linking strands of uniform molecular weight into a network by endgroup coupling reactions? A higher tensile strength has been reported for endlinked networks of polyisoprene in comparison with randomly-crosslinked networks of similar average strand length (4). However, those measurements were not made under threshold conditions and did not examine a wide range of strand lengths, so that direct comparison with molecular theory is not possible.

Measurements have now been carried out on endlinked and randomly-linked samples of polybutadiene, polydimethylsiloxane, and randomly-linked samples of cis-polyisoprene. The results are presented here.

Experimental Details

(i) Endlinked PDMS

Linear polydimethylsiloxanes with vinyl endgroups were supplied by Dow Corning Corporation. Three different molecular weight ranges were employed. Membrane osmometry yielded values for \bar{M}_n of 16,000, 24,000, and 37,000 g/g-mole. Endgroup analysis using mercuric acetate (5) gave vinyl contents of 0.47 ± 0.03 , 0.24 ± 0.02 , and

(3)

0.15 ± 0.02 per cent, corresponding to values for M_n of 11,500, 22,500 and 36,000 g/g-mole. GPC data gave M_w/M_n ratios of approximately 2.0, as reported by Valles and Macosko (6,7) for their similar polymers.

Trifunctional and tetrafunctional silane linking agents were supplied to us by Prof. Macosko. They consisted of trikis-dimethylsiloxyphenylsilane and tetrakis-dimethylsiloxyphenylsilane and are denoted here A3 and A4, respectively. Gas chromatography, carried out by Prof. Macosko, revealed that they were approximately 95 and 89 per cent pure. Si-H group analysis (5) gave average functionalities of 3.15 and 3.50, somewhat different from the expected values of 3 and 4, indicating that other constituents are present.

The linking agent, A3 or A4, was mixed in various concentrations with the divinyl-PDMS, together with 5 ppm of a Pt catalyst (8). The mixture was then degassed and cast as a thin sheet on a Teflon surface. Complete reaction was found to occur on heating for about 3 days at 70°C, as judged by equilibrium swelling measurements in benzene; thereafter, 4 days at 70°C was used to ensure complete reaction.

As shown in Figure 1, values of M_c calculated from equilibrium swelling ratios in benzene (9), were found to depend strongly upon the concentration of endgroups in the linking agent relative to those in the polymer. The highest effective degree of crosslinking, i.e., the lowest degree of swelling and the lowest value for M_c , was obtained at

(4)

a characteristic endgroup ratio lying between about 1.1 and 1.6 instead of the expected ratio of 1.0. Thus, even when allowance is made for the true functionality of the linking agent, it is still necessary to employ a greater amount than expected to produce a minimum value for M_c . Presumably, a significant fraction of polymer endgroups do not become linked into the network until an excess of linking agent is present. This implies that the junction points are not exclusively trifunctional or tetrafunctional in nature.

Networks were prepared in all cases using the amount of endlinking agent necessary to give a minimum M_c . Values of M_c were calculated from the Mooney-Rivlin elasticity coefficient C_1 , determined from tensile stress-strain measurements (10),

$$M_c = \rho RT / 2C_1, \quad (2)$$

where ρ is the density, 0.97 g/ml, R is the gas constant and T is absolute temperature, for comparison with earlier work (2).

(ii) Randomly - crosslinked PDMS

The polydimethylsiloxane (PDMS) used to make random networks was obtained from General Electric. Membrane osmometry showed \bar{M}_n to be 430,000 g/g-mole. The polymer was mixed with various amounts of a free-radical crosslinking agent, dicumylperoxide (Di-Cup R, Hercules Chemical Co.). Samples were then pressed into sheets and crosslinking was effected by heating for 2 h at 150°C in a heated press. M_c values were calculated using equation 2.

(5)

(iii) Endlinked PB

Endlinked polybutadiene samples were provided by Prof. F. N. Kelley and Mr. Long-Ji Su of these laboratories. They were made by reacting toluene -2,4- diisocyanate with the vinyl endgroups of vinyl-terminated polybutadiene (Arco R45-HT) and then employing trimethylolpropane as a trifunctional linking agent. The prepolymer was also chain-extended with 1,4 - butanediol to give a higher M_c value on subsequent endlinking. M_c values, calculated by means of equation 2, were 3,100 g/g-mole for the sample made with the initial polymer and 7,100 g/g-mole when the chain-extended material was used.

(iv) Randomly - crosslinked PB and PI

Polybutadiene (Diene 35 NFA, Firestone Tire and Rubber Co.) and cis-polyisoprene (Natsyn 2200, Goodyear Tire and Rubber Co.) were crosslinked with dicumylperoxide, as for PDMS. M_c values were also calculated by means of equation 2.

(v) Measurements of threshold tear strength

Rectangular strips, about 60 mm long, 10 mm wide and 1.4 mm thick were scored along a central line to a depth of about 0.7 mm, leaving about one-half of the original thickness to be torn through. The tear energy T was calculated from the measured tear force F ,

$$T = 2 F/t, \quad (3)$$

where t is the width of the tear path (Figure 2). Tearing was found to take place at an angle of approximately 45° to the sheet thickness (11).

(6)

Measurements were carried out on both swollen and unswollen samples, using m-xylene or silicone oil as swelling liquids with PDMS networks and m-xylene or paraffin oil with PB and PI networks. Samples were torn at temperatures between 70°C and 140°C. Values of the tear energy T for swollen samples were multiplied by λ_s^2 , where λ_s is the linear swelling ratio, to take into account the reduced number of network strands crossing the tear path (1-3). Close agreement was obtained with unswollen samples at the high temperatures and low rates of tearing (about 4 $\mu\text{m/s}$) used in the present experiments. The mean values have therefore been taken as measures of the threshold tear strength T_0 .

Experimental Results and Discussion

Experimentally-determined values of T_0 for PDMS networks are plotted in Figure 3 against values of M_c calculated from the elastic coefficient C_1 by means of equation 2. T_0 was found to be accurately proportional to $M_c^{1/2}$, in accordance with equation (1), with the coefficient of proportionality K being about 0.30, 0.25, and 0.23 J/m²/ (molecular weight unit)^{1/2} for the A4, A3, and randomly-linked materials, respectively. These differences are small, barely significant, but in the expected direction. Values of T_0 are also shown in Figure 3 for the other materials examined. Again, a proportionality to $M_c^{1/2}$ was found, in accordance with theory. Moreover, the present values for endlinked PB and randomly-linked PI are in good agreement with previously-reported data on randomly-linked PB, with $K = 0.85$ J/m². This is much larger than for the PDMS materials, however. Thus, at the same value of M_c , elastomeric networks based on C-C molecular chains have a threshold strength about three times that of Si-O networks.

Although the bond dissociation energies for C-C and Si-O bonds are quite similar, 89 and 80 kcal/g-mole respectively, the molecular weight per main-chain atom is considerably higher for PDMS (37 molecular weight units) than for PI (17) and PB (13.5). The extended length of a network strand is therefore much smaller for PDMS at the same value of M_c . There are also steric restrictions on straightening the Si-O chain due to unequal main-chain bond angles. Thus, the threshold strength of

PDMS networks would be expected to be less than one-half as large as for C-C networks, in accordance with observation.

Conclusions

The threshold tear strength of elastomeric molecular networks does not appear to depend strongly, if at all, upon the uniformity of network strand lengths. It is found to be proportional to $M_c^{1/2}$ where M_c is the mean molecular weight of the strands, in accordance with the theory of Lake and Thomas (3). However, it is considerably smaller for Si-O networks than for C-C networks at equal M_c values. This is attributed to differences in strand length and extensibility.

Acknowledgements

This work was supported by research grants from the Office of Naval Research (Contract ONR N00014-76-C-0408) and Lord Kinematics Division of Lord Corporation. Professor F. N. Kelley and Mr. L.-J. Su of these laboratories supplied the samples of endlinked polybutadiene. The authors are also indebted to Prof. C. W. Macosko of the University of Minnesota for supplying the endlinking reagents, A3 and A4, and helpful advice on their use, and to Dow Corning Corp. for samples of polydimethylsiloxane polymers having reactive endgroups.

References

1. H. K. Mueller and W. G. Knauss, Trans. Soc. Rheol., 15, 217 (1971).
2. A. Ahagon and A. N. Gent, J. Polym. Sci: Polym. Phys. Ed., 13, 1903 (1975).
3. G. J. Lake and A. G. Thomas, Proc. Royal Soc. (London), A300, 108 (1967).
4. M. Morton and D. C. Rubio, Plastics and Rubber: Mat. Appl. 3, 139 (1978).
5. R. C. Smith, N. C. Angelotti, and C. L. Hanson, "Analysis of Silicones", A. L. Smith, ed., John Wiley & Sons, New York, 1974, p.150.
6. E. M. Valles and C. W. Macosko, Rubber Chem. Technol., 49, 1232 (1976).
7. E. M. Valles and C. W. Macosko, Macromolecules, 13, 521 (1979).
8. C. B. Kauffman and D. O. Cowan in "Inorganic Synthesis", Vol. 6, E. G. Rochow, ed., McGraw-Hill, New York, 1969, p.214.
9. H. Shih and P. J. Flory, Macromolecules, 5, 759 (1972).
10. L. R. G. Treloar, "Physics of Rubber Elasticity", 2nd Ed., Clarendon Press, Oxford, 1958.
11. A. Ahagon, A. N. Gent, H. J. Kim and Y. Kumagai, Rubber Chem. Technol., 48, 896 (1975).

Figure Legends

Figure 1. M_c from equilibrium swelling in benzene vs concentration of A4 endlinking agent in divinyl-PDMS, $M_n = 11,500$.

Figure 2. (a) Tear test (b) Sketch of torn cross-section.

Figure 3. Threshold tear energy T_0 for PDMS networks (O, Δ , \square), PB networks (\bullet , \blacktriangle), and PI networks (\ominus), vs molecular weight M_c between crosslinks calculated from C_1 . Random crosslinking: O, \ominus , \bullet ; trifunctional endlinking: Δ , \blacktriangle ; tetrafunctional endlinking: \square .

(11)

Figure 1.




Figure 2.





Figure 3.



ENERGETIC MATERIALS RESEARCHDISTRIBUTION LIST

	<u>No. Copies</u>		<u>No. Copies</u>
Assistant Secretary of the Navy (R, E, and S) Attn: Dr. R.E. Reichenbach Room 5E787 Pentagon Washington, DC 20350	1	AFATL Eglin AFB, FL 32542 Attn: Dr. Otto K. Heiney	1
Office of Naval Research Code 473 Arlington, VA 22217 Attn: Dr. R. Miller	10	AFRPL Code PACC Edwards AFB, CA 93523 Attn: Mr. W. C. Andrepont	1
Office of Naval Research Code 200B Arlington, VA 22217 Attn: Dr. J. Enig	1	AFRPL Code CA Edwards AFB, CA 93523 Attn: Dr. R.R. Weiss	1
Office of Naval Research Code 260 Arlington, VA 22217 Attn: Mr. D. Siegel	1	Code AFRPL MKPA Edwards AFB, CA 93523 Attn: Mr. R. Geisler	1
Office of Naval Research Western Office 1030 East Green Street Pasadena, CA 91106 Attn: Dr. T. Hall	1	Code AFRPL MKPA Edwards AFB, CA 93523 Attn: Dr. F. Roberto	1
Office of Naval Research Eastern Central Regional Office 495 Summer Street Boston, MA 02210 Attn: Dr. L. Peebles Dr. A. Wood	2	AFSC Andrews AFB, Code DLFP Washington, DC 20334 Attn: Mr. Richard Smith	1
Office of Naval Research San Francisco Area Office One Hallidie Plaza Suite 601 San Francisco, CA 94102 Attn: Dr. P. A. Miller	1	Air Force Office of Scientific Research Directorate of Chemical & Atmospheric Sciences Bolling Air Force Base Washington, DC 20332	1
Defense Technical Information Center DTIC-DDA-2 Cameron Station Alexandria, VA 22314	12	Air Force Office of Scientific Research Directorate of Aero- space Sciences Bolling Air Force Base Washington, DC 20332 Attn: Dr. L. H. Caveny	1
		Anal-Syn Lab Inc. P.O. Box 547 Paoli, PA 19301 Attn: Dr. V. J. Keenan	1

DEF.

	<u>No. Copies</u>		<u>No. Copies</u>
Army Ballistic Research Labs Code DRDAR-BLP Aberdeen Proving Ground, MD 21005 Attn: Mr. L. A. Watermeier	1	Hercules Inc. Eglin AFATL/DL DL Eglin AFB, FL 32542 Attn: Dr. Ronald L. Simmons	1
Army Ballistic Research Labs ARRADCOM Code DRDAR-BLP Aberdeen Proving Ground, MD 21005 Attn: Dr. Ingo W. May	1	Hercules Inc. Magna Bacchus Works P.O. Box 98 Magna, UT 84044 Attn: Mr. E. H. DeButts	1
Army Ballistic Research Labs ARRADCOM Code DRDAR-BLT Aberdeen Proving Ground, MD 21005 Attn: Dr. Philip Howe	1	Hercules Inc. Magna Bacchus Works P.O. Box 98 Magna, UT 84044 Attn: Dr. James H. Thacher	1
Army Missile Command Code DRSME-RK Redstone Arsenal, AL 35809 Attn: Dr. R. G. Rhoades Dr. W. W. Wharton	2	HQ US Army Material Development Readiness Command Code DRCDE-DW 5011 Eisenhower Avenue Room 8N42 Alexandria, VA 22333 Attn: Mr. S. R. Matos	1
Atlantic Research Corp. 5390 Cherokee Avenue Alexandria, VA 22314 Attn: Dr. C. B. Henderson	1	Johns Hopkins University APL Chemical Propulsion Information Agency Johns Hopkins Road Laurel, MD 20810 Attn: Mr Theodore M. Gilliland	1
Ballistic Missile Defense Advanced Technology Center P.O. Box 1500 Huntsville, AL 35807 Attn: Dr. David C. Sayles	1	Lawrence Livermore Laboratory University of California Livermore, CA 94550 Attn: Dr. M. Finger	1
Ballistic Research Laboratory USA ARRADCOM DRDAR-BLP Aberdeen Proving Ground, MD 21005 Attn: Dr. A. W. Barrows	1	Lawrence Livermore Laboratory University of California Livermore, CA 94550 Attn: Dr. R. McGuire	1
Hercules Inc. Cumberland Aerospace Division Allegany Ballistics Lab P.O. Box 210 Cumberland, MD 21502 Attn: Dr. Rocco Musso	2	Lockheed Missiles and Space Co. P.O. Box 504 Sunnyvale, CA 94088 Attn: Dr. Jack Linsk Org. 83-10 Bldg. 154	1

DEF.

	<u>No. Copies</u>		<u>No. Copies</u>
Lockheed Missile & Space Co. 3251 Hanover Street Palo Alto, CA 94304 Attn: Dr. H. P. Marshall Dept. 52-35	1	Naval Research Lab Code 6100 Washington, DC 20375	1
Los Alamos Scientific Lab P.O. Box 1663 Los Alamos, NM 87545 Attn: Dr. R. Rogers, WX-2	1	Naval Sea Systems Command Washington, DC 20362 Attn: Mr. G. Edwards, Code 62R3 Mr. J. Murrin, Code 62R2 Mr. W. Blaine, Code 62R	1
Los Alamos Scientific Lab P.O. Box 1663 Los Alamos, NM 87545 Attn: Dr. B. Craig, M Division	1	Naval Sea Systems Command Washington, DC 20362 Attn: Mr. R. Beauregard SEA 64E	1
Naval Air Systems Command Code 330 Washington, DC 20360 Attn: Mr. R. Heitkotter Mr. R. Brown	1	Naval Surface Weapons Center Code R11 White Oak, Silver Spring, MD 20910 Attn: Dr. H. G. Adolph	1
Naval Air Systems Command Code 310 Washington, DC 20360 Attn: Dr. H. Mueller Dr. H. Rosenwasser	1	Naval Surface Weapons Center Code R13 White Oak, Silver Spring, MD 20910 Attn: Dr. R. Bernecker	1
Naval Explosive Ordnance Disposal Facility Indian Head, MD 20640 Attn: Lionel Dickinson Code D	1	Naval Surface Weapons Center Code R10 White Oak, Silver Spring, MD 20910 Attn: Dr. S. J. Jacobs	1
Naval Ordnance Station Code 5034 Indian Head, MD 20640 Attn: Mr. S. Mitchell	1	Naval Surface Weapons Center Code R11 White Oak, Silver Spring, MD 20910 Attn: Dr. M. J. Kamlet	1
Naval Ordnance Station Code PM4 Indian Head, MD 20640 Attn: Mr. C. L. Adams	1	Naval Surface Weapons Center Code R04 White Oak, Silver Spring, MD 20910 Attn: Dr. D. J. Pastine	1
Dean of Research Naval Postgraduate School Monterey, CA 93940 Attn: Dr. William Tolles	1	Naval Surface Weapons Center Code R13 White Oak, Silver Spring, MD 20910 Attn: Dr. E. Zimet	1
Naval Research Lab Code 6510 Washington, DC 20375 Attn: Dr. J. Schnur	1		

DEF.

6/80

4

	<u>No. Copies</u>		<u>No. Copies</u>
Naval Surface Weapons Center Code R101 Indian Head, MD 20640 Attn: Mr. G. L. MacKenzie	1	Naval Weapons Center Code 388 China Lake, CA 93555 Attn: D. R. Derr	1
Naval Surface Weapons Center Code R17 Indian Head, MD 20640 Attn: Dr. H. Haiss	1	Naval Weapons Center Code 388 China Lake, CA 93555 Attn: Dr. R. Reed Jr.	1
Naval Surface Weapons Center Code R11 White Oak, Silver Spring, MD 20910 Attn: Dr. K. F. Mueller	1	Naval Weapons Center Code 385 China Lake, CA 93555 Attn: Dr. A. Nielsen	1
Naval Surface Weapons Center Code R16 Indian Head, MD 20640 Attn: Dr. T. D. Austin	1	Naval Weapons Center Code 3858 China Lake, CA 93555 Attn: Mr. E. Martin	1
Naval Surface Weapons Center Code R122 White Oak, Silver Spring, MD 20910 Attn: Mr. L. Roslund	1	Naval Weapons Center China Lake, CA 93555 Attn: Mr. R. McCarten	1
Naval Surface Weapons Center Code R121 White Oak, Silver Spring, MD 20910 Attn: Mr. M. Stosz	1	Naval Weapons Support Center Code 5042 Crane, Indiana 47522 Attn: Dr. B. Douda	1
Naval Weapons Center Code 3853 China Lake, CA 93555 Attn: Dr. R. Atkins	1	Rohm and Haas Company 723-A Arcadia Circle Huntsville, Alabama 35801 Attn: Dr. H. Shuey	1
Naval Weapons Center Code 3205 China Lake, CA 93555 Attn: Dr. L. Smith	1	Strategic Systems Project Office Dept. of the Navy Room 901 Washington, DC 20376 Attn: Dr. J. F. Kincaid	1
Naval Weapons Center Code 3205 China Lake, CA 93555 Attn: Dr. C. Thelen	1	Strategic Systems Project Office Dept. of the Navy Room 1048 Washington, DC 20376 Attn: Mr. E. L. Throckmorton Mr. R. Kinert	2
Naval Weapons Center Code 385 China Lake, CA 93555 Attn: Dr. A. Amster	1	Thiokol Chemical Corp. Brigham City Wasatch Division Brigham City, UT 84302 Attn: Dr. G. Thompson	1

DEF.

6/80

5

	<u>No. Copies</u>		<u>No. Copies</u>
USA ARRADCOM DRDAR-LCE Dover, NJ 07801 Attn: Dr. R. F. Walker	1	Georgia Institute of Technology Office of Research Administration Atlanta, Georgia 30332 Attn: Professor Edward Price	1
USA ARRADCOM DRDAR-LCE Dover, NJ 07801 Attn: Dr. N. Slagg	1	Univ. of Utah Dept. of Mech. & Industrial Engineering MEB 3008 Salt Lake City, Utah 84112 Attn: Dr. Stephen Swanson	1
U.S. Army Research Office Chemistry Division P.O. Box 12211 Research Triangle Park, NC 27709	1	Space Sciences, Inc. 135 Maple Avenue Monrovia, CA 91016 Attn: Dr. M. Farber	1
Institute of Polymer Science University of Akron Akron, OH 44325 Attn: Professor Alan N. Gent	1	Washington State University Dept. of Physics Pullman, WA 99163 Attn: Professor G.D. Duvall	1
SRI International 333 Ravenswood Avenue Menlo Park, CA 94025 Attn: Dr. Y.M. Gupta	1	Univ. of Maryland Department of Mechanical Eng. College Park, MD 20742 Attn: Professor R.W. Armstrong	1
Graduate Aeronautical Lab. California Institute of Technology Pasadena, CA 91125 Attn: Professor W.G. Knauss	1	The Catholic University of America Physics Department 520 Michigan Ave., N.E. Washington, D.C. 20017 Attn: Professor T. Litovitz	1
Pennsylvania State University Dept. of Mechanical Engineering University Park, PA 16802 Attn: Professor Kenneth Kuo	1	Sandia Laboratories Division 2513 P.O. Box 5800 Albuquerque, N.M. 87185 Attn: Dr. S. Sheffield	1
Office of Naval Research 800 N. Quincy St. Arlington, VA 22217 Attn: Dr. G. Neece Code 472	1	IBM Research Lab. K42.282 San Jose, CA 95193 Attn: Dr. Thor L. Smith	1
Thiokol Corp. Huntsville Huntsville Div. Huntsville, AL 35807 Attn: Mr. J.D. Byrd	1	California Institute of Tech. Dept. of Chemical Engineering Pasadena, CA 91125 Attn: Professor N.W. Tschoegl	1
Washington State University Dept. of Physics Pullman, WA 99163 Attn: Prof. T. Dickinson	1	Northwestern University Dept. of Civil Engineering Evanston, IL 60201 Attn: Professor J.D. Achenbach	1
University of California Dept. of Chemistry 405 Hilgard Avenue Los Angeles, CA 90024 Attn: Prof. M.F. Nicol	1	Office of Naval Research Structural Mechanics Program Arlington, VA 22217 Attn: Dr. N.L. Basdekas, Code 474	1

DEF.

No. Copies

University of California 1
Berkeley, CA 94720
Attn: Prof. A.G. Evans

Texas A&M Univ. 1
Dept. of Civil Engineering
College Station, TX 77843
Attn: Professor Richard A. Schapery

SRI International 1
333 Ravenswood Ave.
Menlo Park, CA 94025
Attn: Mr. M. Hill

Los Alamos Scientific Laboratory 1
Los Alamos, NM 87545
Attn: Dr. J.M. Walsh

Rockwell International 1
12214 Lakewood Blvd.
Downey, CA 90241
Attn: H. M. Clancy, Mail Stop AB 70

ONR Resident Representative 1
Ohio State University Research Center
1314 Kinnear Road
Columbus, Ohio 43212
Attn: Joseph Haggard, Department
of the Navy

END

DATE
FILMED

5 - 8 - 1

DTIC

